

ASLAN BE 233, ASLAN BE 234

The book protection film for structured surfaces

The self-adhesive book covering film for structured surfaces ensures a long durability of books. It gives an optimal protection against soiling and prolongs the durability of a book. Not only books but also print products such as drawings, maps or music sheets become easily cleanable.

Due to a reduced initial adhesive tack the films are easily correctable during the application.

ASLAN BE 233 - glossy
ASLAN BE 234 - matt

For any further information please contact our technical advisory service:
+49 (0) 2204.708-80

Construction

face-film:	soft PVC	
thickness:	~ 80 µm	
adhesive:	acrylic pressure adhesive	thickness: ~ 25 µm
release liner:	silicone paper	square weight: ~ 63 g/m ²

Characteristics

adhesive strength: (ASTMD-903)	immediately: The final adhesive strength is, depending on the surface, reached within 24-48 hours.	~ 4.5 – 6 N / 25 mm
dimensional stability:	applied onto aluminum after 48 hours stored at 70 °C (25 x 25 cm)	max. -0.75 %
combustibility:	Stuck on aluminium, the film is self-extinguishing.	
temperature:	application temperature: service temperature range:	min. 15°C -30 °C up to +80 °C
cold resistance:	approx. -5°C	

ASLAN, Schwarz GmbH & Co. KG
Oberauel 2 · 51491 Overath · Germany
phone +49 (0) 2204.708 80 · **fax** +49 (0) 2204.708 50
e-mail info@ASLAN-Schwarz.com



www.ASLAN-Schwarz.com

ASLAN 
EXPERTISE IN SELF-ADHESIVE FILMS

ASLAN BE 233, ASLAN BE 234

Processing

application:	The film must be applied dry.
storage life:	Before application the films can be stored for minimum of 3 years from date of
production.	This only applies if the film is stored at room temperature of 15-25 °C and a relative humidity of the air of 50-60%. To avoid pressure points appearing on the roll surface, we recommend the rolls be stored either vertical standing or for this purpose designed 'hanging' racks.

State: 09|2013

All technical data and advice is based on our experience and measured testing that we believe to be reliable. It remains the customer's responsibility to test the suitability of our products for the intended purpose.

The quality of our products is regularly examined, upgraded and developed. We take the right, without prior notice, to adjust, upgrade and improve the chemical structures or physical characteristics of our products in accordance with our latest knowledge.

ASLAN, Schwarz GmbH & Co. KG

Oberauel 2 · 51491 Overath · Germany

phone +49(0)2204.708 80 · **fax** +49(0)2204.708 50

e-mail info@ASLAN-Schwarz.com



www.ASLAN-Schwarz.com

ASLAN®

EXPERTISE IN SELF-ADHESIVE FILMS