

UltraTack Transparent ASLAN DFP 06

Transparent digital printing film with extra strong adhesion for difficult surfaces

With extra strong adhesion, this transparent, polymeric softened digital printing film is perfect for long-term applications requiring rock-solid, permanent adhesion. These include "hard-to-stick" substrates like non-polar surfaces such as rough or uneven areas as well as low surface energy materials (e.g. dividers or plastic waste bins).

The silicone paper liner, PE-coated on both sides, provides high resistance to moisture and heat and guarantees optimum printing results.

Thanks to the film's transparency, even hard-to-stick surfaces can be designed with sharply defined, cut-out motifs, without time-consuming plotting. Incorporating very detailed graphics, fade-out colour gradients or the look of the surface into the design also becomes possible with this strongly adhesive film for almost any substrate.

To significantly extend the life of your prints, we recommend our PremiumProtect ASLAN SL 17 and PremiumProtect Matt ASLAN SL 18 laminates. They are ideal for use with the UltraTack range and offer protection from UV-rays, the weather and mechanical wear.

For further information or questions regarding special applications please contact our technical advisory service: **+49 2204.708-80**

Construction

Face film:	PVC, polymeric, transparent	
Thickness:	~ 80 µm	
Adhesive:	pressure sensitive polyacrylate	square quantity: ~ 35 g/m ²
Release liner:	double sided PE coated paper	square weight: ~ 140 g/m ²

Characteristics

Adhesive strength (ASTM D903):	applied on stainless steel immediately: after 1 week:	~ 12,5 N/25mm ~ 22 N/25mm
Dimensional stability:	applied onto aluminium after 48 hours stored at 70 °C (158 °F) (25 x 25 cm)	max. -0,45%
Chemical resistance:	In a preece test of 24 hours the applied film is resistant to most petroleum based oils, greases and aliphatic solvents, mild acids, alkaline and salts.	
Light proofness:	DIN 53 388	non-fade grade: 7-8 (wool-scale)
Combustibility:	Classified to Euroclass flame retardant standard DIN EN 13501-1, B-s1, d0	
Toy safety:	Classified to the standard for toy safety DIN EN 71- 3	
Temperature:	application temperature: service temperature range:	min 5 °C (41 °F) -30 °C (-22 °F) up to +80 °C (176 °F)
Durability:	Up to 7 years outdoors, with vertical exposure, in central European standard climatic conditions.	

UltraTack Transparent ASLAN DFP 06

Processing

Printability:	The material is printable with solvent, eco-solvent, UV-curable and latex inks as well as with screen printing inks. In case of inadequate drying of the print-inks the film will be sodded and the adhesive negatively affected.
Application:	<p>Application dry or wet. If applied wet, a whitening of the adhesive can occur, but will disappear after a couple of days depending on the weather conditions.</p> <p>We recommend to perform a test application before applying the film onto surfaces with a non-stick coating such as box bodies for trailers, which are made out of plywood material, or plastic waste bins.</p> <p>For wet applications we recommend the transfer liquid ASLAN TL10. For the application of lettering etc. we recommend our ASLAN application tapes, respectively the ASLAN TMO.</p>
Gloss:	There can be matt areas on the surface of the highly glossy film near the core of the roll. These can be caused by the rear of the backing paper, but will disappear after a short period of time and do not influence the print results.
Storage:	Before application the films can be stored up to 2 years from date of production. The film must be stored at room temperature (15-25 °C / 59-77 °F) and a relative humidity of the air of 50-60%. To avoid pressure points appearing on the roll surface, we recommend the rolls be stored either vertical standing or for this purpose designed 'hanging' racks.

State 09|2021

All technical data and advice is based on our experience and measured testing that we believe to be reliable. It remains the customer's responsibility to test the suitability of our products for the intended purpose.

The quality of our products is regularly examined, upgraded and developed. We take the right, without prior notice, to adjust, upgrade and improve the chemical structures or physical characteristics of our products in accordance with our latest knowledge.